



- Approved and tested sarking membrane, many years of practical experience for increased requirements
- Proof against wind, water and driving rain, can be exposed to the weather for 4 months
- Efficient installation with two-way integrated self-adhesive strips and verified system accessories

## Delivery form

Roll width [m]	Roll length [m]	Roll area [m <sup>2</sup> ]	Roll weight [kg]
1.5	50.0	75.0	14
3.0	25.0	70.0	14

## Field of application



## Technical data

Material	Three-layer polypropylene composite	
Thickness [mm]	0.50	
Vapour diffusion resistance coefficient $\mu$	110	
$s_d$ value [m]	0.05	
Fire behaviour (EN 13501-1)	Class E	
Specific weight [g/m <sup>2</sup> ]	150	
Waterproofing	W1	
Temperature resistance [°C]	-40 to +100	
Minimum installation temperature [°C]	0	
Stretch [%]	lengthwise	70
	across	80
Maximum tensile force [N/5cm]	lengthwise	300
	across	220
Resistance to tearing (nail shank) [N]	lengthwise	210
	across	210
CE	EN 13859-1	

## Product description

PAVATEX ADB is a permeable sarking membrane with two-way integrated self-adhesive strips. It is used on PAVATEX sarking boards and with PAVATEX over-rafter insulation systems on SWISSTHERM/PAVATHERM and SWISSTERM-COMBI/PAVATHERM-COMBI.

Usage according to regulations and standards<sup>1)</sup>

The longitudinal joints are glued using the integrated two-way self-adhesive strips. The transverse joints are glued with PAVATAPE 12. Screws and nails are sealed with PAVAFIX SN BAND. Connections and penetrations are sealed with PAVATEX sealing products.

If mechanically secured, PAVATEX ADB can be left exposed to the weather for 4 months.

## Storage

Store the rolls dry and cool, lying down or upright, protected from sunshine and humidity.

<sup>1)</sup> Please observe the country-specific application areas according to the regulations and standards in the technical documentation.



## PAVATEX System accessories

PAVACOLL 310/600  
 PAVABOND  
 PAVAFIX  
 PAVATAPE 12  
 PAVATAPE FLEX  
 PAVAFIX SN BAND

*You will find details on usage and installation guidelines in the sealing brochure.*

