



Baumit SV 61

Renovation spatterdash mortar

Product	Factory prepared dry powder mortar in accordance with DIN 18557 and DIN EN 998-1. Certified cement renovation spatterdash mortar acc. to WTA for manual and machine application.		
Intended use	As part of the Baumit renovation renders system. Baumit SV 61 spatterdash mortar provides a keying coat on to damp, salt-contaminated masonry substrates (brickwork, natural stone) to improve adhesion and equalize background suction. The product is generally applied sporadically (50-60% coverage) but is also be applied as a full coating on to masonry with sulphate contamination or gypsum materials.		
Composition	Sand, sulphate resistant binders and additives to enhance special physical properties and improve workability and adhesion.		
Properties	Mineral based renovation spatterdash mortar with good water retention capacity and good adhesion to the substrate. Easy hand or machine application. Optimised strength and high capillary performance suited to the conditions of damp, salt contaminated masonry. The product may also be used on new masonry.		
Technical data	Strength class:	CS IV acc. to DIN EN 998-1	
	Compression strength:	> 6 N/mm ²	
	Aggregate size:	0-4 mm	
	Water vapour diffusion resistance μ :	< 15	
	Water penetration:	> 5 mm after 1 h, < 20 mm after 24 h	
	Water requirement:	6 - 7 l/sack	
	Consumption:	c. 5 - 6 kg/m ² / (50-60% sporadic coat) c. 9 - 10 kg/m ² / (50-60% full coat)	
	Yield:	c. 18 l/sack	
Health and safety	Risk hazards:	H315:	Causes skin irritation.
		H318:	Causes severe damage to eyes.
	Safety phrases:	P102:	Keep out of the reach of children.
		P280:	Wear protective gloves / protective clothing / eye protection / face protection.
		P305+P351+ P338+P310:	IN CASE OF EYE CONTACT: rinse carefully with water for several minutes. Remove contact lenses if possible. Continue rinsing. Immediately call a POISON CENTRE or physician.
		P302+P352+ P332+P313:	IF ON SKIN: Wash with plenty of soap and water. If skin irritation occurs get medical advice / attention.
		P362:	Remove contaminated clothing and wash before reuse.
	Low in chromate for at least 6 months from date of manufacture when stored correctly.		
Quality assurance	Continual monitoring and inspection of the quality of all raw materials upon reception. The manufacturer has a TÜV tested and certified Quality Management System in accordance with the international standard EN ISO 9001 and a TÜV tested and certified Environmental Management System in accordance with the international standard EN ISO 14001.		
Packaging	Paper sacks, 35 kg. 1 pallet = 36 sacks = 1260 kg		
Storage	Store in dry conditions and protected on pallets for up to 6 months.		

Product Data Sheet

Substrate	<p>Remove old render up to 1 metre above the level of dampness. Rake out friable mortar joints 20-30mm deep. Remove dirt, dust and bitumen. Remove and replace loose or damaged masonry. Thoroughly clean masonry (compressed-air guns or wire brushing etc). Dampen high suction backgrounds with clean water. A good bonding to the substrate must be achieved.</p>
Application	<p>Refer to the salt analysis and procedure documentation! Do not mix Baunit SV 61 with other materials. The product is mixed with clean water for no longer than 3 minutes to a slurry consistency with an electric hand mixer or a continuous horizontal mixer or a forced action mixer. Over-mixing will reduce the mortar strength. Do not remix material which has set. Standard mortar mixing pumps are also suitable to mix and spray apply the product. Use worn rotor and stators (coarse sharp aggregates) and lubricate the spray hoses with a lime slurry before pumping the product.</p> <p>Spray or hand apply Baunit SV 61 on to the substrate as a spatterdash coat covering 50-60% of the substrate surface. A full coat application (where appropriate) should be 5 mm thick. The product should not be used as a leveling coat. Do not allow the coating to dry too quickly. Dampen the finished work at regular intervals with a water mist sprayer to aid hydration. The subsequent render system should be applied after 1-2 days for good adhesion.</p>
Further information	<p>Protect the facade from direct sunlight, rain and strong winds (i.e. with scaffold nets) until fully cured. In hot and/or windy weather dampen the finished work at regular intervals with a water mist sprayer to aid hydration. High air humidity and low temperatures can prolong drying times considerably. Dehumidifiers or good ventilation is required in closed rooms to enable the spatterdash to dry out. Allow to cure for 1-2 days. Longer standing time on damp masonry can cause a laitance to form on the spatterdash surface leading to adhesion problems for subsequent coatings. Protect other materials such as glass, ceramics or metal etc from contamination with appropriate coverings. Clean tools immediately with clean water after use.</p> <p>The air, material and background temperature must be above +5° C and below +30° C during application and curing. Observe the WTA guidelines and DIN EN 998-1, DIN V 18550 and DIN 18350 (VOB, Part C).</p>

This Product Data Sheet has been issued by:

The information contained in this product data sheet together with any additional written or verbal information provided by Baunit is based on Baunit's previous experience of this product and reflects Baunit's current understanding of the properties of the product. However, the Customer acknowledges that the advice given in this product data sheet is not intended to be legally binding nor to create any obligation which is legally enforceable against Baunit. It is the customer's responsibility to make its own enquires and investigations into the properties and use of this product and to verify that the product is fit for the customer's intended use. Baunit reserves the right to make changes to the product without prior notice.

Baunit UK Ltd 4200 Waterside Centre, Solihull Parkway Birmingham Business Park, Birmingham. B37 7YN
tel.: +44 (0) 333-358 3434, email: info@baunit.co.uk web.: www.baunit.co.uk